



Mycosynthesis of Silver Nanoparticles, Their Characterization and Antimicrobial Activity

Hemant Bhangale¹, Dilip Patil^{*2}

¹JDMVP's Arts, Commerce and Science College, Yawal, Maharashtra, India

²Nanomaterial Research Laboratory, R.C. Patel ACS College, Shirpur, Maharashtra, India

ABSTRACT

The use of the Fungus *Penicillium* species for the synthesis of silver nanoparticles was discussed in the present paper. The prepared nanoparticles were characterized by using UV-visible spectrophotometry, X-ray diffraction analysis, Transmission Electron Microscopy. The surface plasmon resonance peak observed at 413 nm in UV-visible spectra confirm the formation of silver nanoparticles. (TEM) images revealed that the particles were spherical with size in the range between 11 nm to 20 nm. Surface area electron diffraction pattern revealed the crystalline nature of silver nanoparticles with face centred cubic geometry. The synthesized silver nanoparticles were evaluated for the antimicrobial activity against Gram Positive bacteria *B. Subtilis* and displayed the zone of inhibition 24.19 mm in diameter.

Keywords: Biosynthesis, silver nanoparticles, UV-visible spectroscopy, TEM, antimicrobial activity.

I. INTRODUCTION

The assembly of atoms or molecules bound together in a diameter or size in the range between 1nm to 100 nm[1] form the nanoparticles. Particles having the size greater than 2 nm are known as nano crystal while the particles with the size less than 2nm are nanoclusters. Due to exclusive optical, electrical, and electronic properties of metal nanoparticles, they found applications in various fields like agriculture, medicine, catalysis [2], sensing, bioimaging etc. Silver and its compounds are known for their practice in antimicrobial activities. It is well known that silver nanoparticles exhibited excellent optical, electrical and thermal properties, hence useful in various fields such as sensing, catalysis, bioimaging, medical, agriculture etc. The antimicrobial activity of the silver nanoparticles against Gram-positive and Gram negative bacteria such as *S. Aureus* [3,], *B. Subtilis* [4], *E. coli* [5] etc.

The conventional physical and chemical methods are found to be hazards as they are using toxic chemicals in the preparation of nanoparticles. Also, these methods require bulky and expensive instruments. Hence

biological methods are important for the synthesis of nanoparticles as these methods are simple, environmentally benign. This technique involve the use of plants extract and microorganisms, algae, bacteria fungi, etc. Among these use of microorganism fungi is becoming more popular because of its simplicity in the growth mechanism, fast growth of biomass, rapid synthesis and large-scale production.

Fungi such as *Fusarium oxysporum* [6], *Aspergillus Flavus*[7,8], *Aspergillus Niger*[9] etc. have shown their ability for the extracellular synthesis of silver nanoparticles.

Here we report the rapid synthesis of silver nanoparticles which exhibit good antimicrobial activity against *B. Subtilis*.

II. MATERIALS AND METHODS

Chemical and Ingredients

Silver nitrate was purchased from Sigma Aldrich. Potato dextrose broth was used of HI media. The fungus culture *penicillium* species (NCIM 1313) was obtained from

National Chemical Laboratory culture collection centre, Pune.

Synthesis of silver nanoparticles

The cell filtrate of the fungus *penicillium* species was prepared as described by Hemath et. al.[10].For the preparation of silver nanoparticles 25 ml of cell filtrate was mixed with equal amount of 1mM AgNO₃ in Erlenmeyer flask. The flask was then kept in an orbital shaker and incubated at 110 rpm for 24 h.

Characterization of silver nanoparticles

The formation of silver nanoparticles was observed visually and then confirmed by using UV-visible spectrometer (Shimadzu 2450) scanning in the range between 200 nm to 800 nm. For structural information the synthesized silver nanoparticles were subjected to X-ray diffraction analysis. The information about size and morphology of the silver nanoparticles was achieved from Transmission electron microscope. For this purpose, a drop of colloidal solution of silver nanoparticles was kept on carbon coated copper grid and allowed to dry in air to form a film. The formed film was used for TEM characterization. The antimicrobial activity of silver nanoparticles was evaluated against *Staphylococcus aureus* by disc diffusion method. The sample disc P16 impregnated with 100 µl of colloidal solution of silver nanoparticles was placed on nutrient agar plates and incubated at 37°C for 24 h.

III. RESULT AND DISCUSSION

UV-visible spectroscopic measurements



Figure 1. Cell filtrate treated with AgNO₃




Figure 2(a). UV-visible spectra of Cell filtrate




Figure 2(b). UV-visible spectra of cell filtrate with AgNO₃

The change in colour of the reaction medium from pale yellow to brown within 24 h was the first indication for the formation of the silver nanoparticles. Figure 2(a) shows the UV-visible spectra of the cell filtrate with the absorption peak appeared at 260 nm which may be attributed to aromatic amino acids of proteins[11]. Figure 2(b) depicts the UV-visible spectra of the cell filtrate treated with 1 mM silver nitrate solution. It displayed the surface plasmon resonance peak at 413 nm

which is the characteristic signature of the silver nanoparticles[12].

Transmission Electron Microscopy

TEM micrographs are presented in figure 5 revealed that the synthesized particles were spherical in shape and in the size range between 11 nm to 20 nm. The particles were well dispersed but with some agglomeration. SAED pattern of the silver nanoparticles shown in Figure 5 specified that the particles were crystalline in nature with face centered cubic structure.




Figure 3(a). TEM image of synthesized silver nanoparticles




Figure 3 (b). SAED pattern of Ag NPs

Antimicrobial Activity



Figure 4. Antimicrobial activity of AgNO₃

The antibacterial activity of the synthesized silver nanoparticles was shown in figure 6. The zone of inhibition of diameter 24.77 mm corresponding to the sample disc P16 exhibit the antibacterial performance of silver nanoparticles.

IV. CONCLUSION

The cell filtrate of *Penicillium* species have the ability for extracellular synthesis of silver nanoparticles in lesser time. These nanoparticles were found to be spherical in the size range 11 nm to 20 nm as revealed from the TEM images. SAED pattern indicates the crystalline nature of silver nanoparticles with fcc geometry. The antimicrobial activity exhibited by the nanoparticles have shown their potential for the alternative to present antibiotics in the field of pharmaceuticals.

V. REFERENCES

- [1]. Jayasmita Jana, Mainak Ganguly and Tarasankar Pal, Royal Society of Chemistry, DOI: 10.1039/C6RA14173K,2016,6,86174-86211.
- [2]. Liangwei Du, Qiuhong Xu, Meiyong Huang, liang Xian, Jia-Xum Feng, material Chemistry and Physics,xxx,20151-8.
- [3]. Dattu Singh, Vandana Rathod, Shivaraj Ningangouda, Jyoti Hiremath, Ashish Kumaar Singh, and Jasmine Mathew, Bioinorganic Chemistry and Applications, 2014,8pages.
- [4]. Achintya Mohan Goswami, Tuhin Subhra Sarkar and Sanjay Ghosh, AMB Express 2013,3:16,1-9.
- [5]. Deepak K. Rahi and Aruna S. Parmar , International Journal of Nanomaterials and Biostructures, 2014;4(3): 46-51.

- [6]. Ahamad A., Mukherjee P., Senapati S.,Mandal D.Khan M.I. Kumar R., Colloids Surface B. Biointerfaces 28,313-318,2003.
- [7]. Navin Jain ,Arpit Bhargava, Sonali Majumdar, J.C. Tarafdar and Jitendra Panwar, Nanoscale ,2011,3,635-641.
- [8]. R.Manimozhi, R. Anitha,bInternational Journal of Pharmaceutics and Drug Analysis,Vol.2,issue 9,2014,734-739
- [9]. A.K. Gade,P.Bonde,A.P. Ingale,P.D.Marcato,N.Duran,and M.K.Rai,Journal of Biobased Materials and Bioenergy,vol.2,2008,1-5.
- [10]. Hemath Naveen K.S., Gaurav Kumar, Karthik L., Bhaskara- Rao K.V., Achieves of Applied Reserch, 2010,2(6),161-167.
- [11]. D Soheyla Honary, H. Barabadi, E.G. Fathabad and F.Naghibi,Tropical Journal of Pharmaceutical Research,2013,12(1):7-11].
- [12]. Pitark Jm, Silkin VM, Chulkov EV, Echenique PM, J Optic Pure Applied Optic 2005,7,73-84.