

Comparison of Free Length Thermodynamically and Acoustically of alpha-Alumina (α -Al₂O₃) Nano Suspension in Ethanol Base Fluid

P. D. Bageshwar¹, V. K. Jadhao² and N. R. Pawar³

¹Department of Physics, Mungsaji Maharaj Mahavidyalaya, Darwaha, Maharashtra, India

²Department of Physics, B. B. Arts, N. B. Commerce and B. P. Science College, Digras, Maharashtra, India

³Department of Physics, Arts, Commerce and Science College, Maregaon, Maharashtra, India

*Corresponding Author : pdbageshwar@gmail.com

ABSTRACT

The present paper reports the comparison of free length thermodynamically and acoustically of alpha alumina (α -Al₂O₃) nano suspension in ethanol base fluid. α -Al₂O₃ nanoparticles were synthesized through alkoxide route using sol-gel method. Intermolecular free length has been calculated by thermo acoustical method at different temperatures over the entire range of concentrations and compared with the valued obtained from well established thermodynamic method. The ultrasonic velocity measurement at 4 MHz with an interferometric technique has been made on alpha alumina (α -Al₂O₃) nano suspension in ethanol base fluid. Measurement was taken for the density. The intermolecular free length was calculated from the velocity and density measurements. Free length is related with the surface of nanoparticles and nanoparticle surfactant interactions and help for the study of thermo acoustic and thermodynamic properties of nanosuspension.

Keywords : α -Al₂O₃, Ethanol, Free Length, Nanosuspension

I. INTRODUCTION

Extensive use of free length has been made to study the attraction and repulsion forces between the nanoparticles in nanosuspension. Thermo acoustically free length of nanoparticles in nanosuspension is given by, $L_f = K (\beta a)^{1/2} = K/U\rho^{1/2}$

Where βa , U and ρ respectively the adiabatic compressibility, ultrasonic velocity and density of nanoparticles in suspended medium. The constant K is called Jacobson's constant, which depends on temperature. Jacobson determined the value of K empirically between 0 and 50°C.

Thermodynamically, free length of nanoparticles in nanosuspension is given by,

$$L_f = 2V_a/A$$

Where V_a and A represents the available volume and the surface area of nanoparticles in nanosuspension. Also,

$$V_a = V - V_0$$

$$A = (36\pi N V_0^2)^{1/3}$$

Where N is the Avogadro number V_0 , and V is the molar volume at zero temperature and at temperature T , respectively.

Thermodynamically, the value of V_a can be calculated using critical temperature from the following relation,

$$V_a = V [1 - (1 - T/T_c)^{0.3}]$$

Where T_c is the critical temperature.

The free length has been widely used to interpret the interactions between nano suspensions in the base fluid. There has been an increasing interest in the study of interactions between the nanoparticles in the suspended medium [1-2]. Ultrasonic study of nanosuspension has been extensively carried out in different branches of science to measure the thermodynamic properties to predict the nature of interactions of nanosuspension in base fluid [3-4]. Ultrasonic velocity and thermo acoustic parameters as a function of the concentration in nanoparticle suspension are useful in gaining insight into the structure and bonding of associated nano complexes and other processes in nanosuspension. The materials of interest in this study are α - Al_2O_3 and ethyl alcohol (C_2H_5OH). Thus ethyl alcohol has an OH group that might be expected to lead to the formation of a hydrogen-bonded nano complex with α - Al_2O_3 at the oxygen site and perhaps electrostatic bonding at the other sites. These types of nanosuspension are of interest to organic chemists who want to know about the type of bond and the number of each kind of nanoparticles in the α - Al_2O_3 nano complex.

In this work, measurements of free length acoustically and thermodynamically are functions of concentration and temperatures are reported. The data presented may stimulate other researchers to consider the interactions of nanoparticles in nanosuspension. Such data are valuable in building a core of basic information about nanosuspension. The method used in the measurement of ultrasonic velocity at 4 MHz was the interferometric method over the temperature range 25-40°C.

The main objective of present work is to contribute the free length of α - Al_2O_3 nanosuspension properties database in current literature in order to better understand the effects of various parameters such as

particle size and temperatures. Free length is highly dependent on specific surface area of nanoparticle in nanosuspension.

II. EXPERIMENTAL AND METHODS

The test liquid samples used were spectroquality. All these samples are of BDH analar grade and were assume to be sufficiently pure so that no further purification was necessary. In this study the ultrasonic measurements have been made by interferometric method at fixed frequency 4 MHz over the entire range of concentrations and in the temperature range 25 – 40°C. The velocity of ultrasound thus measured was accurate to within 0.01%. The densities were measured with an Anton Paar DMA 35 N vibrating tube densimeter with a $\pm 0.5 \times 10^{-3} g/cm^3$ resolution. The temperature of nanosuspension medium was controlled to within 0.2°C. Nanoparticles of alpha alumina (α - Al_2O_3) was prepared by sol-gel method [6-11] from Aluminum isopropoxide [$Al(OC_3H_7)_3$] and aluminum nitrate. The average particle size α - Al_2O_3 has been estimated by using Debye-Scherrer formula. The average estimate size of α - Al_2O_3 nano particles is found to be 20-30 nm Pawar et.al. The prepared α - Al_2O_3 nano particles were suspended in ethanol.

III. RESULTS AND DISCUSSION

The intermolecular forces, which in one way or another determine the said properties of nanosuspension, consist of attractive forces and repulsive forces. These forces have opposite directions but are numerically equal under given external conditions. The attractive forces are dependent on the distance between what are called the centres of attraction of the nanoparticles, whereas the repulsive forces are dependent on the distance between the surfaces of the nanoparticles. Centres of attraction do not coincide with the geometrical centre of the nanoparticles. The distances between the surfaces have a clear physical significance, and thus lend themselves

more easily. Surface tension, viscosity, thermal expansion and molecular association will be related to the intermolecular free length. The acoustic wave which was excited in the nano suspended medium is momentarily to the intermolecular length. Free length is long, ultrasonic velocity has a low value. Its value corresponded to the molecular shape Fig.11 contains the plot of free length computed acoustically versus molar concentration. It shows similar trend as that of adiabatic compressibility and reverse trend as that of ultrasonic velocity which is in good agreement with the theoretical requirement.




Figure.1 Free length versus molar concentration of α - Al_2O_3 nanosuspension in ethanol

IV. CONCLUSION

1. The free length computed acoustically and thermodynamically shows considerable deviation from any linear variation with respect to molar concentrations.
2. Non linear variation of free length versus molar concentration is due to Brownian motion of nanoparticles in nanosuspension.
3. Behavior of nanoparticles in ethanol base fluid nano suspension dependent on its specific surface area.
4. Free length study of nanoparticles in nanosuspension highly useful in understanding nature of interactions, internal structure and the aggregation behavior.

V. REFERENCES

- [1]. D.H. Kumar, H.E. Patel, V.R.R. Kumar, T. Sundararajan, T. Pradeep, S.K. Das, Model for heat conduction of nanofluids, *Physical Review Letters*, 2004, 94, 14, 1-3.
- [2]. S. Rajagopalan, S. J. Sharma and V. Y. Nanotkar, Ultrasonic Characterization of Silver Nanoparticles, *Journal of Metastable and Nanocrystalline Materials* 2005, 23 271-274.
- [3]. Gan Z, Ning G, Lin Y, Cong Y, Morphological control of mesoporous alumina nanostructures via template-free solvothermal synthesis. *Mater Lett* 2007, 61, 31, 3758–3761.
- [4]. Zhan X, Honkanen M, Leva E Transition alumina nanoparticles and nanorods from boehmite nanoflakes. *J Crystal Growth*, 2008, 310, 30, 3674–3679.
- [5]. Y. K. Park, E. H. Tadd, M. Zubris, and R. Tannenbaum, Size controlled synthesis of alumina nanoparticles from aluminum alkoxides, *Materials Research Bulletin*, 2005, 40, 9, 1512.
- [6]. D. G. Wang, F. Guo, J. F. Chen, H. Liu, and Z. Zhag, Preparation of nano aluminium trihydroxide by high gravity reactive precipitation, *Chemical Engineering Journal*, 2006, 121, 2-3, 109-114.
- [7]. R. Aghababazadeh, A. R. Mirhabibi, J. Pourasad, A. Brown, A. Brydson, and N. Ameri Mahabad, Economical synthesis of Nanocrystalline alumina using an environmentally low-cost binder, *Journal of Surface Science*, 2007, 601,13,2864-2867
- [8]. P. Christian and M. Bromfield, Preparation of small silver, gold and copper nanoparticles which disperse in both polar and non-polar solvents, *J. Mater. Chem*, 2010, 20, 1135 – 1139.
- [9]. Rogojan R, Andronescu E, Ghitulica C, Stefan B, Synthesis and characterization of alumina nano-powder by sol-gel method. *UPB Sci Bull Ser B* , 2011, 73, 2, 27, 67–76.

- [10].Bhalla V., Kumar R., Tripathi S. and Sing D., Mechanical and thermal properties of praseodymium nanoparticles: an ultrasonic study, *Int. J. Mod. Phys. B*, 2013, 27, 1350116.
- [11].Pawar N. R., Ph.D thesis Summary on Investigation of Ultrasonic wave absorption in some Bio-liquids, *J Pure and Appl Ultrasonic*, 2014, 36, 69.
- [12].Pawar N. R. and Chimankar O. P., Comparative Study ultrasonic absorption and relaxation behavior of polar solute and non-polar solvent, *Pure and Appl Ultrasonic*, 2015, 37, 11.
- [13].Johari G K & Mishra R L, *Acustica*, 1984, 56, 66.